



17025 SO. MAIN ST. GARDENA, CA 90248 310.217.2378
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstonedealer.com

MATERIAL PRODUCT DATA SHEET

Product Name

Classic Pilaster Cap

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete since 1963. Classic Pilaster Caps provide distinctive good looks with high strength hardrock concrete. The Classic Pilaster Cap has a 2" bullnose edge with a ¼" top and bottom reveal. Classic Pilaster Caps are designed to be used for both commercial and residential applications.

Composition & Materials

Classic Pilaster Caps are hand-made, wet-cast from 4000 PSI hardrock concrete using Type III cement.

Sizes

Classic Pilaster Caps are available in standard sizes; 10"x18" (Flat only), 14"x14", 16"x16", 19"x19", 22"x22", 24"x24", and 28"x28" Flat Classic Pilaster Caps have a thickness of 2 ½ "; peaked Classic Pilaster Caps thickness varies. Please see Classic Pilaster Cap details for more detailed size information.

Finishes

Classic Pilaster Cap finishes include: standard smooth finish and Veranostone® sandblast

Colors

Classic Pilaster Caps are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

Physical / Chemical Properties

Classic Pilaster Cap weight is a minimum of 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

June 2024