



17025 SO. MAIN ST. GARDENA, CA 90248 310.217.2378
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstonedealer.com

MATERIAL PRODUCT DATA SHEET

Product Name

Classic Pool Coping

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete since 1963. Classic Pool Coping provides distinctive good looks with high strength hardrock concrete. The Classic Pool Coping has a 2" bullnose edge with a ¼" top and bottom reveal. They work well as a design element to refine pool & spa projects. The system includes straights, inside corners, outside corners and radius components. Classic Pool Coping is designed to be used for both commercial and residential applications.

Composition & Materials

Classic Pool Copings are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

Sizes

Pool Coping straights are 14"x24"x2½"; corners are 14"x16"x2½"; radius components vary. Please see Classic Pool Coping details for more detailed size information.

Finishes

Classic Pool Coping available in finishes include: fine grain stipple and Veranostone® sandblast

Colors

Classic Pool Copings are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

Physical / Chemical Properties

Classic Pool Coping is 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

February 2025