



17025 SO. MAIN ST. GARDENA, CA 90248 310.217.2378  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstonedealer.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Modern Garden Step

### Manufacturer

Stepstone, LLC  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-217-2378  
Fax 310-694-9060  
Toll Free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete since 1963. Modern Garden Steps provide distinctive good looks with high strength hardrock concrete. The Modern Garden Step has a 2" bullnose edge. They work well as a design element to refine any project. The system includes straights and corners. They are designed to be used for both commercial and residential applications.

### Composition & Materials

Modern Garden Steps are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

### Sizes

Modern Garden Step straights are 18"x24"x2" and 18"x18"x2"; corners are 18"x18"x2". All sizes include bullnose.

### Finishes

Modern Garden Step available finishes include: fine grain stipple and Veranostone® sandblast

### Colors

Modern Garden Steps are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

### Physical / Chemical Properties

Modern Garden Steps weight is 22 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, LLC for further information*

February 2025