



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

MATERIAL PRODUCT DATA SHEET

Product Name

Modern Garden Step

Manufacturer

Stepstone, Inc.
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete for over 40 years. Modern Garden Steps provide distinctive good looks with high strength hardrock concrete. The Modern Garden Step has a 2" bullnose edge. They work well as a design element to refine any project. The system includes straights and corners. They are designed to be used for both commercial and residential applications.

Composition & Materials

Modern Garden Steps are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

Sizes

Modern Garden Step straights are 18"x24"x2" and 18"x18"x2"; corners are 18"x18"x2". All sizes include bullnose.

Finishes

Modern Garden Step available finishes include: fine grain stipple and Veranostone® sandblast

Colors

Modern Garden Steps are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

Physical / Chemical Properties

Modern Garden Steps weight is 22 LBS per square foot. Water absorption: Not more than 6.0% average, not more than 7.0% for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, Inc. for further information

September 2019