



17025 SO. MAIN ST. GARDENA, CA 90248 310.217.2378
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstonedealer.com

MATERIAL PRODUCT DATA SHEET

Product Name

Hexagonal Paver

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete since 1963. Hexagonal Pavers are precast concrete pavers that come in many standard sizes. Hexagonal Pavers are designed to be used for both commercial and residential applications.

Composition & Materials

Hexagonal Pavers are hand-made, wet-cast from 4000 PSI hard rock concrete using Type III cement.

Sizes

Hexagonal Pavers are available in standard sizes. 16" pavers are 1 ¾" thick; 20 ½" and 24" are 2 ½" thick. All sizes are nominal. Corner and Starter pieces also available. Please see Hexagonal Paver details for more size information.

Finishes

Hexagonal Pavers available finishes include: Veranostone® or Hermosastone®

Colors

Hexagonal Pavers are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

Physical /Chemical Properties

Hexagonal Paver weight is 20 LBS PSF for 1 ¾" thickness and 28 LBS PSF for 2 ½" thickness. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

February 2025