



17025 SO. MAIN ST. GARDENA, CA 90248 | 310.217.2378
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstonedealer.com

MATERIAL PRODUCT DATA SHEET

Product Name

Sonorastone® Paver

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete since 1963. Sonorastone® Pavers are precast concrete pavers that are available in 6 standard sizes. They are designed to be used in a variety of ways for commercial and residential applications.

Composition & Materials

Sonorastone® Pavers are hand-made, wet-cast from 4000 PSI hardrock concrete using Type III cement.

Sizes

Sonorastone® is available in standard sizes: 11-7/8"x11-7/8"x2", 11-7/8"x23-7/8"x2", 11-7/8"x35-7/8"x2", 17-7/8"x17-7/8"x2", 17-7/8"x23-7/8"x2", 17-7/8"x35-7/8"x2", 23-7/8"x23-7/8"x2", 23-7/8"x35-7/8"x2"

Finishes

Sonorastone® Paver available finishes include: slate texture or sandblasted slate texture.

Colors

Sonorastone® Pavers are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

Physical / Chemical Properties

Sonorastone Paver weight is 22 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

February 2025