



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Sonorastone® Wall Cap

### Manufacturer

Stepstone, Inc.  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-217-2378  
Fax 310-694-9060  
Toll Free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete for over 40 years. Sonorastone® Wall Caps provide distinctive good looks with high strength hardrock concrete. They work well as garden bench seats or as a design element to refine wall appearance. The system includes straights, corners, ends, radius pieces and special pilaster caps. Sonorastone® Wall Caps are designed to be used for both commercial and residential applications.

### Composition & Materials

Sonorastone® Wall Caps are hand-made, wet-cast from 4000 PSI hardrock concrete using Type III cement.

### Sizes

Sonorastone® Wall Cap is available in standard sizes: Peaked: 9-1/4", 12-1/4", 16-1/4"; Flat: 7-1/4", 9-1/4", 13-1/4" widths; straight lengths are 24"; thickness varies.

### Finishes

Sonorastone® Wall Cap available finishes include: slate texture or sandblasted slate texture.

### Colors

Sonorastone® Wall Caps are available in 18 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

### Physical / Chemical Properties

Sonorastone® Wall Cap weight is a minimum of 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.