



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Square Modular Pool Coping

### Manufacturer

Stepstone, Inc.  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-217-2378  
Fax 310-694-9060  
Toll Free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete for over 40 years. Square Modular Pool Coping provides distinctive good looks with high strength hardrock concrete. The Square Modular Pool Coping has a 2½" square edge. They work well as a design element to refine pool & spa projects. The system includes straights and corners. Square Modular Pool Coping is designed to be used for both commercial and residential applications.

### Composition & Materials

Square Modular Pool Copings are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

### Sizes

Pool Coping straights are 12x24"x2½", 16"x24"x2½", 16"x36"x2½"; corners are 16"x16"x2½".

### Finishes

Square Modular Pool Coping available in finishes include: fine grain stipple and Veranostone® sandblast

### Colors

Square Modular Pool Copings are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

### Physical / Chemical Properties

Square Modular Pool Coping is 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, Inc. for further information*

September 2019