



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

MATERIAL PRODUCT DATA SHEET

Product Name

Square Modular Wall Cap

Manufacturer

Stepstone, Inc.
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete for over 40 years. Square Modular Wall Caps provide distinctive good looks with high strength hardrock concrete. They work well as garden bench seats or as a design element to refine wall appearance. The system includes straights, corners, ends and pilaster caps. Square Modular Wall Caps are designed to be used for both commercial and residential applications.

Composition & Materials

Square Modular Wall Caps are hand-made, wet-cast from 4000 PSI hardrock concrete using Type III cement.

Sizes

Square Modular Wall Cap is available in standard sizes: Straights, Ends, Corners 9-1/4", 13-1/4", 20-1/4" straight lengths are 24"; corner and radius lengths vary. Square Modular Wall Caps have a thickness of 3-3/8".

Finishes

Square Modular Wall Cap available finishes include: smooth finish or Veranostone® (light sandblast)

Colors

Square Modular Wall Caps are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

Physical / Chemical Properties

Square Modular Wall Cap weight is a minimum of 38 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, Inc. for further information

September 2019