



17025 SO. MAIN ST. GARDENA, CA 90248 310.217.2378
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstonedealer.com

MATERIAL PRODUCT DATA SHEET

Product Name

Truncated Dome Paver

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll free 800-572-9029

Product Description

Stepstone, Inc. has produced high quality pre-cast concrete since 1963. Truncated Dome Pavers are precast, A.D.A. compliant, detectable warning surface pavers that are designed to be used in commercial as well as public works applications. Pavers have an aligned dome pattern.

Composition & Materials

Truncated Dome Pavers are hand-made, wet-cast from 4000 PSI hard rock concrete using Type III cement.

Sizes

Truncated Dome Pavers are available in the standard sizes 11-7/8" x 11-7/8" x 2" and 23-7/8" x 23-7/8" x 2".

Finishes

Truncated Dome Pavers available finishes include: Domed stippled finish or Veranostone® sandblast

Colors

Truncated Dome Pavers are available in 15 standard colors: Custom Federal Yellow FS 33538, Yellow, Charcoal, Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors are available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

Physical/Chemical Properties

Truncated Dome Paver weight is 22 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

February 2025