



17025 SO. MAIN ST. GARDENA, CA 90248 | 310.217.2378  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstonedealer.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Veranostone® Narrow Modular Paver

### Manufacturer

Stepstone, LLC  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-217-2378  
Fax 310-694-9060  
Toll free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete since 1963. Veranostone® Narrow Modular Pavers are precast concrete pavers that come in five standard sizes. Veranostone® Narrow Modular Pavers are designed to be used for both commercial and residential applications.

### Composition & Materials

Veranostone® Narrow Modular Pavers are hand-made, wet-cast from 4000 PSI hard rock concrete using Type III cement.

### Sizes

Veranostone® Narrow Modular Pavers are available in 3" x 9" x 4", 3" x 12" x 4", 3" x 18" x 4" and 3" x 24" x 4"

### Finishes

Veranostone® Narrow Modular Pavers available finishes include: Veranostone® Sandblast

### Colors

Veranostone® Narrow Modular Pavers are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors available upon request; minimum order required.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM E303 - *Pendulum Slip Resistance*

### Physical /Chemical Properties

Veranostone® Narrow Modular Pavers: 4" thickness is 48 PSF; Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Not interlocking pavers; see installation details. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, LLC for further information*

February 2025