



Precast Solutions Since 1963

17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

MATERIAL PRODUCT DATA SHEET

Product Name

Veranostone® Paver

Manufacturer

Stepstone, Inc.
17025 So. Main St.
Gardena, CA 90248

Phone 310-217-2378
Fax 310-694-9060
Toll free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete for over 40 years. Veranostone® Pavers are precast concrete pavers that come in many standard sizes. Veranostone® Pavers are designed to be used for both commercial and residential applications.

Composition & Materials

Veranostone® Pavers are hand-made, wet-cast from 4000 PSI hard rock concrete using Type III cement.

Sizes

Veranostone® Pavers are available in standard sizes ranging from 12" x 12" to 18" x 36" in 1-3/4" thickness. Please see Veranostone® Paver details for standard sizes.

Finishes

Veranostone® Pavers available finish: Light sandblast

Colors

Veranostone® Pavers are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Café Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain. Custom colors are available upon request; minimum order required.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

Physical /Chemical Properties

Veranostone® Paver weight is 20 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, Inc. for further information

September 2019